



nobonobo[®]

Natural fabrics collection

NOBONOBO | **PIEVA** | natural fabric



Fiber composition: 14% LI 67% VI 16% CO 3% PL
Weight: 780g/M2 +/-5%
Martindale test: >20 000 cykli
Color fastness to light: 4/5 - 5
Color fastness to rubbing: dry 4-5, wet 4-5
Pilling: test (scale 1/5) 4/5




PIEVA 1



PIEVA 2



PIEVA 3




PIEVA 4



PIEVA 5

NOBONOBO | SINA | natural fabric




Fiber composition: 31% CO 53% VI 11% LI 5% PA
Weight: 1070g/M2 +/-5%
Martindale test: >45 000 cykli
Color fastness to light: 4/5 - 5
Color fastness to rubbing: dry 4-5, wet 3/4
Pilling: test (scale 1/5) 4/5



SINA 1



SINA 2



SINA 3



SINA 4



SINA 5

NOBONOBO | **FRIGO** | natural fabric



Fiber composition: 22% LI 72% VI 6% CO
Weight: 725g/M2 +/-5%
Martindale test: >30 000 cykli
Color fastness to light: 4/5 - 5
Color fastness to rubbing: dry 4-5, wet 3/4
Pilling: test (scale 1/5) 4/5



FRIGO 1



FRIGO 2



FRIGO 3



FRIGO 4



FRIGO 5



FRIGO 6


NOBONOBO | **SPESSA** | natural fabric




Fiber composition: 15% LI 53% VI 23% CO 7% PL 2% PC
Weight: 840g/M2 +/-5%
Martindale test: >25 000 cykli
Color fastness to light: 4/5 - 5
Color fastness to rubbing: dry 4/5, wet 3/4
Pilling: test (scale 1/5) 4/5



SPESSA 1



SPESSA 2



SPESSA 3



SPESSA 4




SPESSA 5

NOBONOBO | **PULSANO** | natural fabric



Fiber composition: 39% CO 28% PL 4% LI 8% VI 21% PC
Weight: 800g/M2 +/-5%
Martindale test: >25 000 cykli
Color fastness to light: 4/5 - 5
Color fastness to rubbing: dry 4/5, wet 3/4
Pilling: test (scale 1/5) 4/5



PULSANO 1




PULSANO 2



PULSANO 3



PULSANO 4



PULSANO 5

BRIONNE | natural fabric



Fiber composition: 18%CO, 31%PL, 26%WO, 22%PC, 3%PA
Weight: 740 gr/m2
Martindale test: 40 000 cykli
Color fastness to light: 4/5 - 5
Color fastness to rubbing: dry 4/5, wet 2/3
Pilling: test (scale 1/5) 3/4



BRIONNE 385.010



BRIONNE 385.020



BRIONNE 385.000




BRIONNE 385.001



BRIONNE 385.031




BRIONNE 385.041



BRIONNE 385.040


BARBAT | natural fabric



Fiber composition: 41%PC, 38%PL, 21%CO
Weight: 762 gr/m2
Martindale test: 40 000 cykli
Color fastness to light: 3 - 5
Color fastness to rubbing: dry 4/5, wet 3
Pilling: test (scale 1/5) 4/5



BARBAT 18



BARBAT 17



BARBAT 16



BARBAT 15



BARBAT 1



BARBAT 10



BARBAT 14



BARBAT 12



BARBAT 24



BARBAT 7




BARBAT 2




BARBAT 4

ELISSOS | natural fabric



Fiber composition: 30%PL, 28%PC, 21%VI, 12%CO, 9%LI
Weight: 860 gr/m2
Martindale test: 30 000 cykli
Color fastness to light: 3 - 5
Color fastness to rubbing: dry 4/5, wet 3
Pilling: test (scale 1/5) 4



ELISSOS 1



ELISSOS 2



ELISSOS 3




ELISSOS 5



ELISSOS 6



ELISSOS 8



ELISSOS 10



ELISSOS 13



ELISSOS 14



ELISSOS 15



ELISSOS 17



ELISSOS 19



ELISSOS 22