


nobonobo®



Textile collection

AMARAL / ANGHELI / ASSIOMA / DIAMOND / FRIDA / GRETA / HUGO / ILEO / MOLIA / MOMBASA / MYSTIC /
NURIEL / PERSEMPRA 4 / PETRA / SELMA / SIMONE / SPIRIT

AMARAL

Martindale test: 60 000 cycles

Color fastness to light: 4-5



Color fastness to rubbing: 5

Pilling: test (scale 1/5) 5




Fiber composition:

96% PL, 4% CO

Weight: 551 g/m²




AMARAL 56





AMARAL 395



AMARAL 407




AMARAL 60




AMARAL 347




AMARAL 300



AMARAL 271



AMARAL 10



AMARAL 710

ANGHELI

Martindale test: 100 000 cycles
Color fastness to light: 4/5
Color fastness to rubbing:
dry 4, wet 3/4
Pilling: test (scale 1/5) 4

Fiber composition:
51% PL, 36% CO, 13% VI
Weight: 665 g/m²



ANGHELI 101



ANGHELI 101



ANGHELI 102



ANGHELI 103




ANGHELI 104



ANGHELI 105



ANGHELI 106



ANGHELI 107



ANGHELI 108




ANGHELI 109



ANGHELI 110



ANGHELI 111




ANGHELI 112



ANGHELI 113



ANGHELI 114



ANGHELI 115



ANGHELI 116



ANGHELI 117




ANGHELI 118




ASSIOMA


Martindale test: 100 000 cycles
Color fastness to light: 5
Color fastness to rubbing:
dry 4/5, wet 4
Pilling: test (scale 1/5) 4/5

Fiber composition:
45% PL, 35% CO, 20% PC
Weight: 824 g/m²



ASSIOMA 1








DIAMOND





Martindale test: 100 000 cycles
Color fastness to light: 4/5
Color fastness to rubbing:
dry 4, wet 3/4
Pilling: test (scale 1/5) 4



Fiber composition: 48% PL, 40% CO
12% VI
Weight: 781 g/m²



DIAMOND 101







FRIDA

Martindale test: 100 000 cycles

Color fastness to light: 5

Color fastness to rubbing:


dry 4-5, wet 4

Pilling: test (scale 1/5) 3/4


Fiber composition:

42% PL, 30% PC, 28% CO


Weight: 750 g/m² ± 5%




FRIDA 01




FRIDA 01




FRIDA 02




FRIDA 03



FRIDA 04



FRIDA 05



FRIDA 06

GRETA

Martindale test: 100 000 cycles
Color fastness to light: 5
Color fastness to rubbing:
dry 4/5, wet 4/5
Pilling: test (scale 1/5) 4

Fiber composition:
95% PL, 5% PC
Weight: 600 g/m² ± 5%



GRETA 01



GRETA 01



GRETA 02



GRETA 03



GRETA 04



GRETA 05




GRETA 06




GRETA 09



GRETA 07



GRETA 08



GRETA 10



GRETA 11



GRETA 12



GRETA 13



GRETA 14



GRETA 15

HUGO

Martindale test: 100 000 cycles

Color fastness to light: 5


Color fastness to rubbing:

dry 4, wet 4

Pilling: test (scale 1/5) 4

Fiber composition: 100% polyester

Weight: 710 g/m² ± 5%




HUGO 01




HUGO 01




HUGO 02




HUGO 03




HUGO 04




HUGO 05



HUGO 06



HUGO 07



HUGO 08

ILEO

Martindale test: 100 000 cycles

Color fastness to light: 4/5

Color fastness to rubbing:


dry 4-5, wet 4-5

Pilling: test (scale 1/5) 5




Fiber composition:


58% CO, 42% PL

Weight: 580 g/m² ± 5%



ILEO 5





ILEO 21



ILEO 22



ILEO 11



ILEO 10



ILEO 9



ILEO 8




ILEO 7




ILEO 6



ILEO 17



ILEO 16



ILEO 15




ILEO 14



MOLIA

Martindale test: 50 000 cykli
Color fastness to light: 5
Color fastness to rubbing:
dry 4, wet 3/4
Pilling: test (scale 1/5) 4/5

Fiber composition:
68% PA, 29% PL, 3% VI
Weight: 577 g/m² ± 5%




MOLIA 10



MOLIA 10



MOLIA 09



MOLIA 08



MOLIA 07



MOLIA 12



MOLIA 11



MOLIA 13



MOLIA 14




MOLIA 06




MOLIA 01



MOLIA 02



MOLIA 03



MOLIA 04



MOLIA 05

MOMBASA

Martindale test: 100 000 cycles

Color fastness to light: 4/5

Color fastness to rubbing:

dry 4/5, wet 4

Pilling: test (scale 1/5) 4/5

Fiber composition:

49% PL, 35% VI, 16% CO

Weight: 591 g/m² ± 5%



MOMBASA 1





MOMBASA 10



MOMBASA 11



MOMBASA 12



MOMBASA 13



MOMBASA 14



MOMBASA 15



MOMBASA 16



MOMBASA 17



MOMBASA 18



MOMBASA 19

MYSTIC

Martindale test: > 200 000 cycles

Color fastness to light: 4-5


Color fastness to rubbing:
4-5

Pilling: test (scale 1/5) 5

Fiber composition:

100% PL

Weight: 450 g/m² ± 5%



MYSTIC 324




MYSTIC 1



MYSTIC 324



MYSTIC 250



MYSTIC 50



MYSTIC 51



MYSTIC 32



MYSTIC 18



MYSTIC 3




MYSTIC 252



MYSTIC 52



MYSTIC 104



MYSTIC 73



MYSTIC 62




MYSTIC 64



MYSTIC 161



MYSTIC 38




MYSTIC 8



MYSTIC 56



MYSTIC 65



MYSTIC 66



MYSTIC 5



MYSTIC 373



MYSTIC 503



MYSTIC 514




MYSTIC 105



MYSTIC 136



MYSTIC 112



MYSTIC 12



MYSTIC 21



MYSTIC 213




MYSTIC 313



MYSTIC 214




MYSTIC 13




MYSTIC 15



MYSTIC 59



MYSTIC 7



MYSTIC 131



MYSTIC 144




MYSTIC 114



MYSTIC 69



MYSTIC 61



MYSTIC 387



MYSTIC 187



MYSTIC 395



MYSTIC 68




MYSTIC 11



MYSTIC 311



MYSTIC 602




MYSTIC 510

NURIEL

Martindale test: 60 000 cycles
Color fastness to light: 4-5
Color fastness to rubbing: 4-5
Pilling: test (scale 1/5) 5

Fiber composition:
68% PL, 22% MAC, 10% CO
Weight: 577 g/m² ± 5%



NURIEL 56



NURIEL 56



NURIEL 51




NURIEL 90



NURIEL 349




NURIEL 32




NURIEL 790




NURIEL 732




NURIEL 30



NURIEL 28




NURIEL 305




NURIEL 314




NURIEL 324




NURIEL 342




NURIEL 348




NURIEL 341




NURIEL 60



NURIEL 407




NURIEL 795




NURIEL 395




NURIEL 347




NURIEL 300



NURIEL 271



NURIEL 10




NURIEL 710

PERSEMPRA 4

Martindale test: 165 000 cycles
Color fastness to light: (scale 1/8) 7
Color fastness to rubbing:
dry 4,5, wet 4,5
Pilling: test (scale 1/5) 4,5

Fiber composition: 100% PL
Weight: 650 g/m² ± 5%



PERSEMPRA 4 401




PERSEMPRA 4 401



PERSEMPRA 4 402



PERSEMPRA 4 403




PERSEMPRA 4 404




PERSEMPRA 4 405



PERSEMPRA 4 406



PERSEMPRA 4 407



PERSEMPRA 4 408



PERSEMPRA 4 409





PERSEMPRA 4 422



PERSEMPRA 4 423



PERSEMPRA 4 424







PETRA




Test Martindale: 165 000 cycles
Color fastness to light: (scale 1/8) 7
Color fastness to rubbing:
dry 4,5, wet 4
Pilling: test (scale 1/5) 4,5

Fiber composition: 100% PL
Weight: 650 g/m² ± 5%



PETRA 01








SELMA

Martindale test: 80 000 cycles
Color fastness to light: 3/4
Color fastness to rubbing:
dry 4,5, wet 4
Pilling: test (scale 1/5) 4/5

Fiber composition: 100% PL
Weight: 460 g/m² ± 5%



SELMA 01





SIMONE

Martindale test: 100 000 cycles
Color fastness to light: 5
Color fastness to rubbing:
dry 4/5, wet 4/5
Pilling: test (scale 1/5) 4

Fiber composition: 95% PL, 45% PC
Weight: 600 g/m² ± 5%




SIMONE 01



SIMONE 01



SIMONE 02




SIMONE 03



SIMONE 04



SIMONE 05



SIMONE 06




SIMONE 07

SPIRIT

Martindale test: 95 000 cycles
Color fastness to light: 5
Pilling: test (scale 1/5) 5

Fiber composition: 100% PL
Weight: 460 g/m² ± 5%



SPIRIT 1



SPIRIT 1



SPIRIT 2




SPIRIT 250



SPIRIT 50



SPIRIT 32




SPIRIT 104



SPIRIT 52



SPIRIT 31



SPIRIT 7



SPIRIT 28



SPIRIT 38




SPIRIT 55



SPIRIT 12



SPIRIT 105



SPIRIT 61



SPIRIT 516



SPIRIT 34



SPIRIT 106



SPIRIT 11



SPIRIT 321



SPIRIT 40



SPIRIT 69



SPIRIT 213



SPIRIT 15



SPIRIT 59

nobonobo.pl