

nobonobo[®]

Textile collection

BARBAT / HEKLA

**EX
TR
A**

BARBAT

Martindale test: 40 000 cycles

Color fastness to light: 3-5

Color fastness to rubbing:


dry 4/5, wet 3

Pilling: test (scale 1/5) 4/5



Fiber composition:

41% PC, 38% PL, 21% CO

Weight: 762 g/m² ± 5%



BARBAT 18






HEKLA

Test Martindale: 30 000 cycles
Color fastness to light: 4/5
Color fastness to rubbing:
dry 4, wet 3
Pilling: test (scale 1/5) ≥ 4

Fiber composition: 65% PC, 35% PL
Weight: 870 g/m² \pm 5%




HEKLA 24



HEKLA 24




HEKLA 21




HEKLA 22




HEKLA 2




HEKLA 14




HEKLA 13




HEKLA 12




HEKLA 15



HEKLA 11



HEKLA 9




HEKLA 10




HEKLA 23



HEKLA 16




HEKLA 4



HEKLA 5



HEKLA 8



HEKLA 3



HEKLA 7



HEKLA 6



HEKLA 19



HEKLA 25



HEKLA 18



HEKLA 17



HEKLA 20

nobonobo.pl